

AMERICAN PRIDE®

INTERIOR EGGSHELL LATEX PAINT (101 LINE)

RECOMMENDED USE

For properly prepared interior walls of plaster, wallboard, masonry and tightly adhered wallpaper. Ideal for office buildings, hotel rooms and corridors, nursing homes, schools, hospitals, department stores, apartments, and residences.

This product can be used in occupied areas without typical odor complaints because of the very low odor during application and drying.

RECOMMENDED APPLICATION

New Surfaces:

Non-Bleeding Wood, Plaster:

American Pride Interior Latex Primer

Drywall:

American Pride Interior Latex Primer

Metal:

Not recommended for use on metal door and trim

Ferrous: Anti-Rust Primer

Non-Ferrous: Galvanized & Aluminum Primer

RECOMMENDED REPAINT

See Surface Preparation Section.

EQUIPMENT

| | |
|-----------------------|------------------------------------|
| Conv. Spray: | 40 PSI TIP: 704/FX |
| Airless Spray: | 1800 - 2400 PSI TIP: .015" - .021" |
| Brush: | Polyester or Nylon |
| Roller: | 3/8" Nap Cover |
| Pad: | Standard |

**VOC level as determined within the precision of ASTM*



This product meets Green Seal environmental standards for volatile organic compounds (VOCs) and other ingredients.

THINNER & CLEAN-UP

Thinning is not recommended, but if necessary, use clean water sparingly. Soap and water clean-up.

LIMITATIONS

- Do not apply when air, surface or product temperature is below 50° F (10° C) or if temperature might drop to this level within 4 hours of application.
- Do not apply in temperatures above 90° F (32° C).

PACKAGING

Gallons, 5 Gallons

COLORS

Ready Mix Colors & Tint Bases

NOTES

SPECIFICATION DATA

| | |
|--------------------------------------|---|
| Type: | Acrylic Latex |
| Finish: | Eggshell |
| » Sheen: | 19 Max @ 85° |
| % Solids (varies with color): | |
| » By Weight: | 55 ±2% |
| » By Volume: | 38 ±2% |
| Wt./Gallon: (White only): | 11.48 lbs. |
| Flashpoint: | 212° F (PMCC) |
| VOC lbs./gal (max): | 0* |
| VOC grm/ltr (max): | 0* |
| Thinner: | Water |
| Clean-up: | Soap and Water |
| Dry Time: | |
| » To Touch: | 2 hours |
| » By Volume: | 4-8 hours |
| » To Service: | Overnight |
| Thickness: | |
| » Dry: | 1.5 mil |
| » Wet: | 4.0 mil |
| Coverage: | 400 sq. ft./gal (on smooth surfaces) |
| Flame Spread Rate: | Class A (0-25 on non-combustible surfaces) |